

FIRE-RESISTIVE, NON-FLAMMABLE, NEOPRENE-BASED, CONTACT ADHESIVE FOR VAPOR BARRIER LAPS AND INSULATIONS

DESCRIPTION

CHIL-STIX® FRN CP-82 is a neoprene-based, contact adhesive with exceptional bond strength. It is non-flammable in the wet state and meets the performance requirements of Military Specification MIL-A-3316C, Class 2, Grade A.

USES

CHIL-STIX® FRN CP-82 adhesive is ideal for adhering many types of insulations such as fibrous glass, laminated scrims, foils, many plastic films and various foams, both flexible and rigid. **The solvents in this adhesive will attack polystyrene foams and may attack certain other plastic foams, plastic films and plastic laminates.** CHIL-STIX® FRN CP-82 adhesive effectively adheres the laps of most types of vapor barrier jackets. Because of its superior contact properties, it finds many uses both inside and outside of the insulation industry.

APPLICATION

CHIL-STIX® FRN CP-82 adhesive is best applied by brush.

ADVANTAGES

- CHIL-STIX® FRN CP-82 adhesive is non-flammable in the wet state and fire resistive when dry.
- The dry bond properties of CHIL-STIX® FRN CP-82 make it advantageous for use as a vapor barrier lap adhesive.
- This adhesive is easy to brush.
- It is a fast-drying, neoprene adhesive which actually becomes stronger with age.
- A tight, unbreakable bond is immediately formed upon contact of the two coated surfaces.
- Non-flammable, chlorinated solvents eliminate explosion and fire hazards during application.

CERTIFIED

- Meets NFPA Standard 90A and 90B 25/50 requirements.
- Meets ASTM C916, Type 1.
- Meets requirements for LEED IEQ 4.1 Low-Emitting Materials, Adhesives and Sealants. VOC: 2.2 g/l, less exempt solvents.
- This product has been tested according to ASTM E84 (Surface Burning Characteristics of Building Materials).

COLORS

Light tan

WET WEIGHT (ASTM D1475)

11.1 lbs./U.S. gal. (1.3 kg/liter)

AVERAGE NON-VOLATILE (ASTM D2369)

30% by weight

SERVICE TEMPERATURE RANGE

Temperature to which dry coating is subjected.
-30°F to 200°F (-34°C to 93°C)

APPLICATION TEMPERATURE RANGE

40°F to 100°F (4°C to 38°C)

BONDING TIME

One surface: 0 – 5 Minutes

Contact bond: 20 Minutes – 1 Hour

COVERAGE

Varies with substrate.

150 – 250 sq. ft./U.S. gal. (3.6 – 6.1 m²/liter)

For sealing 2 in. (5.08 cm) wide laps: 600 – 750 linear ft./U.S. gal.
(48 – 60 m/liter)

CLEAN UP

Chlorinated solvents (non-flammable) or xylene (flammable)



ADHESIVES SURFACE BURNING CHARACTERISTICS

Applied to Inorganic Reinforced Cement Board

Flame Spread: 10

Smoke Developed: 0

Tested as applied at a coverage rate of 200 sq. ft./gal.

312U

™ Trademark of H.B. Fuller Construction Products Inc.

Visit us on the web at www.fosterproducts.com

H.B. Fuller Construction Products Inc.

Customer Service
800-832-9002

1105 South Frontenac St.
Aurora, IL 60504

Fax
800-952-2368

ADHESION OF BLANKET INSULATIONS TO DUCTS

All fibrous glass (or other) insulations shall be applied to duct using CHIL-STIX® FRN CP-82 adhesive. Entire sheet metal duct surface shall receive a coat of CHIL-STIX FRN CP-82 adhesive applied at a maximum coverage of 250 sq. ft./gal. (6.1 m²/l).

NOTE TO SPECIFYING ENGINEER

Since an adhesive has no better strength than the material it is adhering, and since most insulations such as fibrous glass tend to delaminate, it is desirable in most cases to use welded pins or adhered clips and retaining washers as useful adjuncts to securement. Such welded pins or clips are usually fastened on 18 – 24 inch (45 – 60 cm) centers and are necessary in duct lining work or across the bottoms of ducts that are being wrapped.

LAPS OF VAPOR BARRIER JACKETS ON PIPE AND DUCT INSULATION

All laps of factory-applied jackets and tapes for butt joints shall be adhered with CHIL-STIX® FRN CP-82 adhesive. Minimum overlaps shall be 2 in. (5.08 cm). Laps should be smooth and continuous.

LAPS OF PRE-SIZED GLASS CLOTH PIPE COVERING JACKETS

All laps of pre-sized glass cloth pipe covering jackets shall be adhered with CHIL-STIX® FRN CP-82 adhesive, smoothing out all wrinkles to ensure a smooth, attractive finish.

Application Guide and Suggested Procedures

1. USE OF MATERIAL

CHIL-STIX® FRN CP-82 is a pigmented adhesive, which should require very little mixing. Sometimes upon standing there will be separation, requiring some mixing before using. **DO NOT THIN.**

Although it will not freeze at low temperatures, it is suggested that CHIL-STIX® FRN CP-82 adhesive not be applied at temperatures lower than 40°F (4°C) due to the possibility of condensation or frosting on metallic surfaces, which retards drying and inhibits bonding. Applications made at temperatures exceeding 100°F (38°C) may result in blistering.

Use only in well ventilated areas. Avoid prolonged breathing of vapors and prolonged or repeated contact with skin.

2. THE CONDITION OF THE SURFACES TO BE COATED

CHIL-STIX® FRN CP-82 adhesive may be applied over almost any type of substrate. It is advisable that metal surfaces be as oil-free as possible. No primer is required over galvanized steel to gain maximum adhesion. Do not apply over wet or damp surfaces, as the adhesion will be affected.

3. APPLICATION

CHIL-STIX® FRN CP-82 adhesive is a brush adhesive. When used as a contact cement, apply CP-82 to both surfaces. Allow it to dry before bonding.

For adhering light density insulation such as fibrous glass blanket to sheet metal duct, the CHIL-STIX® FRN CP-82 adhesive should be brush applied at a maximum coverage rate of 250 sq. ft./gal. (6.1 m²/l). It is not necessary to prime galvanized steel or aluminum.

The insulation should be firmly embedded into the adhesive immediately after the application of the adhesive, making sure there is complete contact. It is advised that the user determine the best bonding period based upon the particular working conditions such as temperature, humidity and air movement. It is suggested that the adhesive be applied in 100% coverage. It is advisable to use mechanical fastening devices such as welded pins, particularly on the bottom of wide ducts or other overhead applications.

The solvents in this adhesive will attack polystyrene foam and might attack certain other plastic foams, films or laminates. The user should determine by prior test that this adhesive may be used with a specific material and under the application conditions which exist.

For adhering the laps of pre-sized glass cloth, the adhesive may be applied to the under side of the lap, and then when tacky, the lap should be firmly adhered working from the center of the section outward to ensure a smooth, surface finish.

For adhering the laps of vapor barrier jackets, as on pipe insulation, it is suggested that the adhesive be applied at a heavier rate than for applying blanket insulation. It is preferable to coat both surfaces of the jacket, or as an alternate, coat the underside (foil side), strike the lap and wait until the adhesive is dry so that none is transferred to the finger when touched. The time allowed for sealing can be as long as several days. Jackets may have adhesive applied to the lap in advance and sealed after the adhesive is dry. In all cases of lap adhesion, it is suggested that the laps be sealed together by working from the center outward, to ensure a smooth, surface finish.

CUSTOMER SERVICE: (800) 832-9002

IMPORTANT: H. B. Fuller Construction Products Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is twelve months from date of shipment to the original purchaser or as otherwise provided on the certificate of analysis.

**For professional use only. Keep out of reach of children.
Consult Safety Data Sheet and container label for further information.**