

PRODUCT DATA SHEET

Super Firetemp L

Super Firetemp L is an inorganic, non-combustible, high-temperature insulation for use in fire protection systems. It can be used in systems operating up to 1800°F (982°C). Composed primarily of lime, silica, and reinforcing fibers. This product is white, essentially dust-free, contains no asbestos, mercury or lead, and meets or exceeds ASTM C 656, Type II Grade 5.

THE ADVANTAGES

- Assured Fire Resistance
- Durable
- Economical

APPLICATIONS

Super Firetemp L has high strength as well as exceptional insulation qualities. It can be readily machined into component parts of many sizes and shapes. Uses include fire-rated enclosures around structural steel, tanks, equipment, fire-rated walls, high temperature ovens and refractory backup.

AVAILABLE FORMS AND SIZES

Thickness ¾", 1", 1½", 2", 2½", 3" (19, 25, 38, 51, 64, 76 mm)
 Sheet Size 4' x 4' (1.22m x 1.22m)
 4' x 8' (1.22m x 2.44m)

Super Firetemp L is available with a sanded finish on one or both sides. The sanded surfaces are smooth and easy to machine.

DIMENSION TOLERANCES

Length and Width +/- 1/8" (3.2 mm)
 Thickness +/- 1/8" (3.2 mm) Sanded One Side
 +/- 1/16" (1.6 mm) Sanded Two Sides

LINEAR SHRINKAGE AFTER 24 HOURS AT TEMPERATURE, %

Temperature °F (°C)	Length	Width	Thickness	Weight Loss
1700°F (927°C)	1%	1%	2.1%	10%

THERMAL CONDUCTIVITY

Mean Temperature		"k"	
°F	°C	Btu • in/(hr • ft² • °F)	W/m • °K
200	93	0.54	0.078
400	204	0.61	0.088
600	315	0.67	0.097
800	427	0.73	0.105



SUPER FIRETEMP L®
OPERATING TEMPERATURE LIMIT: 1800°F (982°C)

SPECIFICATION COMPLIANCE

ASTM C656	Type II, Grade 5
ASTM C795 Corrosion: Austenitic Stainless Steel	Passes
ASTM E72 Panel Strength	Passes
ASTM E84 Surface Burning Characteristics	Flame Spread -0 Smoke Developed -0
ASTM E119 Building Fire Test	1-2 Hours
ASTM E119 Structural Fire Test	1-4 Hours (see chart)
ASTM E136 Non-Combustible	Passes
ASTM E814 Penetration Fire Stop	1-2 hours
UL 263 Fire Testing	1-2 Hours
UL 1479 Penetration Fire Stop	1-2 Hours
NFPA 251 Fire Testing	1-2 Hours
Underwriters Laboratories, Inc. Design Numbers	U447, X307, XR301
Underwriters Laboratories Canada Design Numbers	Z200, Z202
R-Value @ 75°F	2.0 per inch
Density (Avg.)	20 pcf (288 kg/m³)
Maximum Recommended Continuous Service Temp.	1800°F (982°C)
Flexural Strength (Avg.)	260 psi (1793 kPa)
Compressive Strength @10% deformation (Avg.)	450 psi (3103 kPa)
Moisture Content, Normal % of Dry Weight (Avg.)	4%

TYPICAL RATINGS FOR SUPER FIRETEMP L

Use this table to estimate the thickness of Super Firetemp L. The table represents the most common applications. More specific information is available from Industrial Insulation Group. For Structural Steel fire protection, use Super Firetemp L unless the product is going to be exposed to physical abuse such as warehouses, then use Super Firetemp M.

CODE COMPLIANCE

Super Firetemp undergoes stringent tests to comply with some of the toughest fire codes in the US and Canada.



ISO 9000 CERTIFICATION

Super Firetemp L is manufactured under an ISO 9001:2000 registered quality system. This registration, along with regular independent third-party auditing for compliance, is your assurance that all our products deliver consistently high quality.

PRODUCT CERTIFICATION

When ordering material to comply with any government specification or any other listed specification, a statement of that fact must appear on the purchase order. Government regulations and other listed specifications require specific lot testing, and prohibit the certification of compliance after shipment has been made. There may be additional charges associated with specification compliance testing. Please refer to IND-CSP-3 for Certification Procedures and Charges. Call customer service for more information.

UL X307 - ASTM E119 STRUCTURAL FIRE TEST

Rating Hour	Minimum Column Size	Minimum Thickness (in)
1½ hr	TS4x4x0.188	1½"
2 hr	TS8x8x0.25	1½"
2 hr	W4x13	1½"
3 hr	W4x13	2½"
3 hr	W10x49	2"
3 hr	W14x228	¾"
4 hr	W14x228	1"