

Data sheet

Cerablanket[®], Cerachem[®], Cerachrome[®] Blankets

ENGLISH

Description

All three grades of blanket have the same excellent chemical stability compared with their raw materials: Cerafiber, Cerachem Fiber and Cerachrome Fiber spun bulk.

They have excellent strength before and after heating. They have superior acoustic as well as thermal insulation characteristics. Available in a wide range of densities and thicknesses allow for the most effective deployment of the superior thermal characteristics in a wide variety of applications.

Type

Blanket made from high temperature refractory ceramic fibre insulation wool.

Classification temperature

Cerablanket blanket: 1315°C (2400°F)

Cerachem blanket: 1425°C (2600°F)

Cerachrome blanket: 1425°C (2600°F)

The maximum continuous use temperature depends on the application. Unaffected by most chemicals except strong alkalis, phosphoric acid and molybdenum. For further advise please contact your local Morgan Advanced Materials partner.

Typical applications

- Furnace and kiln linings
- Boiler insulations
- Heat treatment temperature control
- Glass furnace crown insulation
- Furnace door seals
- Duct linings
- Pipe insulations
- Thermal barriers for automotive industry
- Insulation for field stress relieving of welds
- High temperature filter media
- Nuclear insulation applications
- Steam and gas turbines insulation

Benefits

- Excellent insulating performance
- Unaffected by most chemicals except hydrofluoric and phosphoric acids and strong alkalis
- Excellent thermal stability: fibers have good resistance to devitrification
- For some applications, it is possible to use Cerachrome blanket above its classification temperature (shrinkage is 5% at 1500°C).
- Low heat storage
- The combination of long spun fibres and the needling operation produce tough, resilient and strong blankets, which resist tearing both before and after heating
- Resistance to thermal shock
- Good sound absorption



Data sheet

Cerablanket[®], Cerachem[®], Cerachrome[®] Blankets

	Cerablanket	Cerachem	Cerachrome
Color	white	white	blue/green
Continuous Use Temperature, °C (°F)	1177 (2150)	1315 (2400)	1371 (2500)
Classification Temperature, °C (°F)	1315 (2400)	1425 (2600)	1425 (2600)
Density, kg/m³ (pcf)	64, 96, 128, 160 (4, 6, 8, 10)	64, 96, 128, 160 (4, 6, 8, 10)	64, 96, 128, 160 (4, 6, 8, 10)
Linear shrinkage, %, EN 1094-I, After 24 hrs, isothermal heating			
1000°C (1832°F)	1.5	-	1.5
1100°C (2012°F)	2.2	-	2.2
1200°C (2192°F)	3	1.0	2.7
1300°C (2372°F)	-	2.0	3.5
1400°C (2552°F)	-	3.5	4
1500°C (2732°F)	-	-	5
Specific Heat Capacity, kJ/kg•K (BTU/lb•F)			
1090°C (1994°F)	1.13 (0.27)	1.13 (0.27)	1.13 (0.27)
Tensile Strength, kPa (psi), EN 1094-I			
Measured Density, kg/m ³ (pcf), 64 (4)	30 (4.35)	30 (4.35)	30 (4.35)
96 (6)	70 (10.15)	70 (10.15)	65 (9.43)
128 (8)	90 (13.05)	90 (13.05)	85 (12.33)
160 (10)	110 (15.95)	110 (15.95)	-
Chemical Analysis, % weight basis after firing			
Alumina, Al ₂ O ₃	46	35	43
Silica, SiO ₂	54	50	54
Zirconia, ZrO ₂	-	15	-
Ferric oxide, Fe ₂ O ₃	-	-	0.15
Chromium oxide, Cr ₂ O ₃	-	-	2.8
Alkalies, Na ₂ O + K ₂ O	-	-	0.1
Other	trace	trace	trace
Thermal Conductivity, W/m•K (BTU•in/hr•ft²), per ASTM C201			
Measured Density, kg/m ³ (pcf)	<u>128 (8)</u>	<u>128 (8)</u>	<u>128 (8)</u>
200°C (300°F)	0.05 (0.35)	0.06 (0.42)	-
400°C (752°F)	0.08 (0.56)	0.1 (0.63)	0.09 (0.62)
600°C (1112°F)	0.19 (0.90)	0.15 (1.04)	0.13 (0.90)
800°C (1472°F)	0.20 (1.4)	0.2 (1.33)	0.18 (1.25)
1000°C (1832°F)	0.28 (1.94)	0.27 (1.87)	0.25 (1.73)
1200°C (2000°F)	0.39 (2.71)	0.34 (2.34)	0.34 (2.34)

Contact

Europe:

 Telephone:
+44 (0) 151 334 4030

 E-mail:
marketing.tc@morganplc.com

North America:

 Telephone:
+1 (706) 796 4200

 E-mail:
northamerica.tc@morganplc.com

South America:

 Telephone:
+54 (11) 4373 4439

 E-mail:
marketing.tc@morganplc.com

Asia:

 Telephone:
+65 6595 0000

 E-mail:
asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773