



Fiberglas™ 700 Series Board

Type 706 and 707

Fiberglass Insulation



Description

Type 706 and Type 707 Series Acoustic Boards are made of inorganic glass fibers with a thermosetting resin binder and formed into rigid rectangular boards.

Both Type 706 and Type 707 come with a smooth surface to accommodate fabrics or surface coating for acoustical wall panels and specialized ceiling applications.

Features

- Resists damage and maintains structural integrity and efficiency
- Mold Resistant per ASTM C1338
- Efficiently reduces sound transmission
- 706 and 707 are lightweight, resilient, easy to handle and fabricate

Physical Properties

Property	Test Method	Value
Nominal Density	ASTM C303	Type 706: 6.0 pcf (96 kg/m ³) Type 707: 7.0 pcf (112 kg/m ³)
Temperature Limitation ¹	ASTM C411	0 to 450°F (-18 to 232°C)
Water Vapor Sorption	ASTM C1104	<2% by weight at 120°F (49°C), 95% R.H.
Surface Burning Characteristics ²	UL 723 ASTM E84 or CAN/ULC S102	Flame Spread Index 10 Smoke Developed Index 10

1. Maximum thickness at 450°F (232°C) - 706 and 707: 4" (102mm).

2. The surface burning characteristics of these products have been determined in accordance with UL 723, ASTM E84 or CAN/ULC-S102. Values are reported to the nearest 5 rating.

Standards, Codes Compliance

- ASTM C612, Mineral Fiber Block & Board Thermal Insulation, Types IA, IB – Types 706 and 707
- Doesn't contain the fire retardant decabrominated diphenyl ether (decaBDE)
- NFPA 90A and 90B

700 Series R-Values at 75°F Mean

Product	Nominal k-Value at thickness		
	1-in.	1.5-in.	2-in.
706	4.3	6.5	8.7
707	4.3	6.5	8.7

Sound Absorption Coefficients

ASTM C423; Mounting: Type A—Material placed against a solid backing.

Product Type	Thickness		Octave Band Center Frequencies, Hz						
	in.	(mm)	125	250	500	1000	2000	4000	NRC
706	1	25	0.01	0.22	0.67	0.97	1.05	1.06	0.75
			0.19	0.78	1.06	1.13	1.06	1.12	1.05
707	1	25	0.04	0.26	0.70	1.01	1.07	1.06	0.75
			0.16	0.82	1.15	1.11	1.03	1.07	1.05

Insulations are available in:

- 24"x48" (610mm x 1,219mm)
- Maximum thickness for both Type 706 and Type 707 is 2" (51 mm)

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- Certified by SCS Global Services to contain an average of 53% recycled glass content, 31% pre-consumer and 22% post-consumer
- Environmental Product Declaration (EPD) has been certified by UL Environment
- Material Health Certificate from Cradle to Cradle Products Innovation Institute
- Health Product Declaration* (HPD)



Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein.

SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

LEED® is a registered trademark of the U.S. Green Building Council.



OWENS CORNING INSULATING SYSTEMS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO, USA 43659

1-800-GET-PINK®
www.owenscorning.com

Pub. No. 10021863-A. Printed in U.S.A. July 2018.
THE PINK PANTHER™ & © 1964–2018 Metro-Goldwyn-Mayer Studios Inc.
All Rights Reserved. The color PINK is a registered trademark of Owens Corning.
© 2018 Owens Corning. All Rights Reserved.

